

Proceso UNE-EN ISO 4063:2011	111 (SMAW) (MMA)	131/135 (GMAW) (MIG/MAG)	14 (GTAW) (TIG/TAG)	12 (SAW)	114 (FCAW-SS)	132/133/136/138 (FCAW-GS)	31 (OFW)
Aceros no aleados y de grano fino	UNE-EN ISO 2560:2010	UNE-EN ISO 14341:2011	UNE-EN ISO 636:2017	UNE-EN ISO 14171:2016	UNE-EN ISO 17632:2016		UNE-EN ISO 20378:2019
Aceros de alta resistencia	UNE-EN ISO 18275:2019	UNE-EN ISO 16834:2012		UNE-EN ISO 26304:2018	UNE-EN ISO 18276:2017		
Aceros resistentes a la fluencia	UNE-EN ISO 3580:2018	UNE-EN ISO 21952:2013		UNE-EN ISO 24598:2013		UNE-EN ISO 17364:2006	UNE-EN ISO 20378:2019
Aceros inoxidables y resistentes al calor	UNE-EN ISO 3581:2016	UNE-EN ISO 14343:2017			UNE-EN ISO 17633:2018		
Níqueles	UNE-EN ISO 14172:2015	UNE-EN ISO 18274:2011			UNE-EN ISO 12153:2012		
Cobres	UNE-EN ISO 17777:2016	UNE-EN ISO 24373:2019					
Aluminios		UNE-EN ISO 18273:2016					
Fundiciones	UNE-EN ISO 1071:2016				UNE-EN ISO 1071:2016		
Magnesios		UNE-EN ISO 19288:2016					
Titanios		UNE-EN ISO 24034:2011					
Recargues duros	UNE-EN 14700:2014						
Fundentes				UNE-EN ISO 14174:2012			
Gases de protección		UNE-EN ISO 14175:2009				UNE-EN ISO 14175:2009	
Electrodos no consumibles			UNE-EN ISO 6848:2015				